

SPECIFICATION AMENDMENTS:

Please amend the paragraphs that appear in the upper half of page 87 of the Specification and that encompass Table C-1 with the following amended paragraphs and Table C-1:

--

Table C-1

		Ex. C-1	Ex. C-2	Ex. C-3	Ref. Ex. C-1	Ref. Ex. C-2
Surface condition		Fine	Fine	Fine	Aggregate	Aggregate
Front surface resistivity Log ( $\Omega$ /sq)	Average	10.28	10.51	10.34	7.01	8.84
	Standard deviation	0.15	0.07	0.03	0.05	0.10
Rear surface resistivity Log ( $\Omega$ /sq)	Average	10.31	10.53	10.37	8.83	10.28
	Standard deviation	0.14	0.07	0.03	0.61	0.14
Volume resistivity Log ( $\Omega$ -cm)	Average	8.63	8.63	8.92	9.64	8.7
	Standard deviation	0.07	0.04	0.06	0.26	0.2
<u>Difference between rear surface resistivity and front surface resistivity</u> <del>in surface resistivities between front and rear surfaces</del>	Index	0.02	0.02	0.03	1.82	1.44
<u>Difference between front surface resistivity and volume resistivity</u> <del>in surface resistivities between front and rear surfaces</del>	Index	1.66	1.88	1.42	-2.62	0.14
CB content (% by weight)		15.1	15.1	15.4	15.7	15.5
Average thickness ( $\mu$ m)		100	100	100	100	100

--